

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1. (Canceled).
2. **(Currently Amended)** ~~A ceramic slurry composition for use in production of a thin green sheet comprising a thickness of 10 μ m or less by extruding the composition into an extruded sheet and stretching the extruded sheet, said composition~~ A ceramic green sheet adapted for an electronic device, the green sheet formed by extruding a slurry composition comprising 20 wt% - 50 wt% of a ceramic powder, 2 wt% - 10 wt% of a polymer having an average molecular weight of 400,000 or more, 0.1 wt% - 2 wt% of a polymer having hydrogen bond-forming functional groups, and 40 wt% - 75 wt% of a solvent, and 1 wt% - 5 wt% of a polymer having an average molecular weight of 400,000 or less, wherein the ceramic green sheet has a thickness of about 10 μ m or less.
3. **(Currently Amended)** ~~The ceramic slurry composition~~ A ceramic green sheet according to claim 2, wherein the polymer having an average molecular weight of 400,000 or more is a polyolefin.
4. **(Currently Amended)** ~~The ceramic slurry composition~~ A ceramic green sheet according to claim 2, wherein the hydrogen bond-forming functional groups are selected from the group consisting of -OH, -COOH, -COOCH₃, -NH₂ and -NHCO.
5. **(Currently Amended)** ~~The ceramic slurry composition~~ A ceramic green sheet according to claim 4,
wherein the polymer having the hydrogen bond-forming functional groups is at least one

polymer selected from the group consisting of polyvinylacetates, ethylene-acrylic acid copolymers, ethylene-ethylacryl copolymers, ethylene methylacryl copolymers, polyacrylic acids, polymethacrylic acids, polylactic acids, polyvinylbutyrals, polyvinyl alcohols, polyvinylamines, amine-derived polymers, polyurethanes, polyureas and polyamides.

6. (Withdrawn) A method for producing a thin green sheet comprising:
extruding a ceramic slurry composition to prepare an extruded sheet;
and stretching the extruded sheet,
wherein the ceramic slurry composition comprises 20~50wt.% of a ceramic powder, 2~10wt.% of a polymer having an average molecular weight of 400,000 or more, 0.1~2wt.% of a polymer having hydrogen bond-forming functional groups, and 40~75wt.% of a solvent.
7. (Withdrawn) A method for producing a thin green sheet comprising:
extruding a ceramic slurry composition to prepare an extruded sheet; and
stretching the extruded sheet,
wherein the ceramic slurry composition comprises 20~50wt.% of a ceramic powder, 2~10wt.% of a polymer having an average molecular weight of 400,000 or more, 0.1~2wt.% of a polymer having hydrogen bond-forming functional groups, 40~75wt.% of a solvent, and 1~5wt.% of a polymer having an average molecular weight of 400,000 or less.
8. (Withdrawn) An electronic device comprising:
dielectric ceramic layers;
internal electrodes interposed between the respective dielectric ceramic layers; and
external electrodes electrically connected to the 10 respective internal electrodes,
wherein the dielectric ceramic layers are 40-layer or more stacks formed by laminating green sheets, with a thickness of 10 μ m or less which are produced in accordance with the method of claim 6 , and the internal electrodes contain conductive components.
9. **(Currently Amended)** ~~The ceramic slurry composition~~ A ceramic green sheet according to claim 2, wherein at least one of the polymer having an average molecular weight of 400,000

or more and the polymer having an average molecular weight of 400,000 or less is a polyolefin.

10-11. (Canceled).

12. **(Currently Amended)** ~~The ceramic slurry composition~~A ceramic green sheet according to claim 2, wherein the solvent comprises at least one of paraffins, decahydronaphthalene, tetrahydronaphthalene, naphtha, mineral spirit, toluene, xylene, hexane, and chloroform.

13. **(Currently Amended)** ~~The ceramic slurry composition~~A ceramic green sheet according to claim 2, wherein the solvent comprises at least one of paraffins, decahydronaphthalene, tetrahydronaphthalene, and chloroform.

14. **(Currently Amended)** ~~The ceramic slurry composition~~A ceramic green sheet according to claim 2, wherein ~~the thin~~the ceramic green sheet is laminated to form a several tens of layer thick stack.